

Soldering Wire

Composition
Proportion :
Sn 99.3
Cu 0.7
Melting point :
217 °C ~ 220 °C

LEAD FREE

50g

TS-99.35050



0.5mm

TS-99.38050



0.8mm

TS-99.3A050



1mm

LEAD FREE

100g

TS-99.35100



0.5mm

TS-99.38100



0.8mm

TS-99.3A100



1mm

LEAD FREE

500g

TS-99.35500



0.5mm

TS-99.38500



0.8mm

TS-99.3A500



1mm

TS-635050



0.5mm

TS-638050



0.8mm

TS-63A050



1mm

LEADED

50g

TS-635100



0.5mm

TS-638100



0.8mm

TS-63A100



1mm

LEADED

100g

TS-635500



0.5mm

TS-638500



0.8mm

TS-63A500



1mm

LEADED

500g

Composition
Proportion :
Sn 63
PB 37
Melting point :
183 °C ~ 184 °C

Including rosin