



ARITEC ELECTRONICS CO., LTD.

安利電子有限公司

No.123/137Fifth AvenueLadkrabang.Chalongkrung.Road Lamplatiew
Ladkrabang , Bangkok 10520


Sample Data Sheet of Ceramic Disc Capacitor (Class II)

Customer Code:

AEC Code:

H222MYES084LF

Figure:



Dimension	(D)	: 8.5	m/m max.
Thickness	(T)	: 5.0	m/m max.
Lead Length	(H)	: 30.0	m/m max.
Insulation	(I)	: 3.0	m/m max.
Lead Space	(F)	: 7.5 ±0.5	m/m
Lead Wire	(d)	: 0.5 ±0.05	m/m

REMARK : F = RoHS

Item/Symbol		Specifications
Instrument: HP4278A	Capacitance Range	1760.0 – 2640.0 pF
Test Frequency: 1KHz		
Test Voltage: 1Vrms	Power Factor (D)	<2.5% (0.025) for YA, YB, ZE
Test Temperature: 25°C		< 5% (0.05) for ZF
Temp. Characteristics	YA ☐ YB ☐ ZE ☐ YE ☒ ZF ☐	
Rated Voltage	50V ☐ 500V ☐ 1KV ☐ 2KV ☒ V ☐	
Tolerance	±5% ☐ ±10% ☐ ±20% ☒ +80%, -20% ☐ ± % ☐	
Marking	E2KV 222M	
Insulation Resistance	10.000 MΩ minimum	
Strength of Terminal	1.5 kgs minimum	
Solder Heat	Temp. 270°C ±5°C Dipping Time: 3±0.5 Sec.	
Solderability	Temp. 235°C ±5°C Dipping Time: 2±0.5 Sec.	

Temp. Characteristics	Temp. Range	Max. Capacitance Change	
		JIS	EIA
YA = Y5E	-25°C to +85°C	A: ±5%	E: ±4.7%
YB = Y5P, 2B ₄	-25°C to +85°C	B: ±10%	P: ±10%
ZE = Z5U, 2E ₄	-25°C to +85°C	E: +20%, -55%	U: +22%, -56%
ZF = Z5V, 2F ₄	-25°C to +85°C	F: +30%, -80%	V: +22%, -82%

Capacitance
Temperature
Characteristics

